

AMENDMENTS TO THE SPECIFICATION

The paragraph starting at page 6, line 3 is amended as follows.

As material 14 passes over roller 88, a backing film 96 from coil 94 is applied to material 14. Backing film 96 prevents the coated material from sticking to itself. The preferred backing film is thermoplastic film made of polyethylene terephthalate ~~terephthalate~~ terephthalate (PET) having a thickness of about 4 mils. Material 14 is wound on coil 78. Coil 78 has uncured epoxy material on the material surfaces, therefore it must be stored in a freezer until the further manufacturing steps (for example, laying down a composite layer and doing the lamination) are ready to be undertaken.